Comparisons of Direct Restorative Dental Materials

COMPARATIVE	1	COMPOSITE RESIN	GLASS IONOMER	RESIN-IONOMER
FACTORS	AMALGAM	(DIRECT AND INDIRECT RESTORATIONS)	CEMENT	CEMENT
General Description	Self-hardening mixture in varying percentages of a liquid mercury and silver-tin alloy powder.	Mixture of powdered glass and plastic resin; self-hardening or hardened by exposure to blue light.	Self-hardening mixture of glass and organic acid.	Mixture of glass and resin polymer and organic acid; self hardening by exposure to blue light.
Principle Uses	Fillings; sometimes for replacing portions of broken teeth.	Fillings, inlays, veneers, partial and complete crowns; sometimes for replacing portions of broken teeth.	Small fillings; cementing metal & porcelain/metal crowns, liners, temporary restorations.	Small fillings; cementing metal & porcelain/metal crowns, and liners.
Resistance to Further Decay	High; self-sealing characteristic helps resist recurrent decay; but recurrent decay around amalgam is difficult to detect in its early stages.	Moderate; recurrent decay is easily detected in early stages.	Low-Moderate; some resistance to decay may be imparted through fluoride release.	Low-Moderate; some resistance to decay may be imparted through fluoride release.
Estimated Durability (permanent teeth)	Durable	Strong, durable.	Non-stress bearing crown cement.	Non-stress bearing crown cement.
Relative Amount of Tooth Preserved	Fair; Requires removal of healthy tooth to be mechanically retained; No adhesive bond of amalgam to the tooth.	Excellent; bonds adhesively to healthy enamel and dentin.	Excellent; bonds adhesively to healthy enamel and dentin.	Excellent; bonds adhesively to healthy enamel and dentin.
Resistance to Surface Wear	Low Similar to dental enamel; brittle metal.	May wear slightly faster than dental enamel.	Poor in stress-bearing applications. Fair in non-stress bearing applications.	Poor in stress-bearing applications; Good in non- stress bearing applications.
Resistance to Fracture	Amalgam may fracture under stress; tooth around filling may fracture before the amalgam does.	Good resistance to fracture.	Brittle; low resistance to fracture but not recommended for stressbearing restorations.	Tougher than glass ionomer; recommended for stress-bearing restorations in adults.
Resistance to Leakage	Good; self-sealing by surface corrosion; margins may chip over time,	Good if bonded to enamel; may show leakage over time when bonded to dentin; Does not corrode.	Moderate; tends to crack over time.	Good; adhesively bonds to resin, enamel, dentine/ post-insertion expansion may help seal the margins.
Resistance to Occlusal Stress	High; but lack of adhesion may weaken the remaining tooth.	Good to Excellent depending upon product used.	Poor; not recommended for stress-bearing restorations.	Moderate; not recommended to restore biting surfaces of adults; suitable for short-term primary teeth restorations.
Toxicity	Generally safe; occasional allergic reactions to metal components. However amalgams contain mercury. Mercury in its elemental form is toxic and as such is listed on prop 65.	Concerns about trace chemical release are not supported by research studies. Safe; no known toxicity documented. Contains some compounds listed on prop 65.	No known incompatibilities. Safe; no known toxicity documented.	No known incompatibilities. Safe; no known toxicity documented.
Allergic or Adverse Reactions	Rare; recommend that dentist evaluate patient to rule out metal allergies.	No documentation for allergic reactions was found.	No documentation for allergic reactions was found. Progressive roughening of the surface may predispose to plaque accumulation and periodontal disease.	No known documented allergic reactions; Surface may roughen slightly over time; predisposing to plaque accumulation and periodontal disease if the material contacts the gingival tissue.
Susceptibility to Post-Operative Sensitivity	Minimal; High thermal conductivity may promote temporary sensitivity to hot and cold; Contact with other metals may cause occasional and transient galvanic response.	Moderate; Material is sensitive to dentist's technique; Material shrinks slightly when hardened, and a poor seal may lead to bacterial leakage, recurrent decay and tooth hypersensitivity.	Low; material seals well and does not irritate pulp.	Low; material seals well and does not irritate pulp.
Esthetics (Appearance)	Very poor. Not tooth colored: initially silver-gray, gets darker, becoming black as it corrodes. May stain teeth dark brown or black over time.	Excellent; often indistinguishable From natural tooth.	Good; tooth colored, varies in translucency.	Very good; more translucency than glass ionomer.
Frequency of Repair or Replacement	Low; replacement is usually due to fracture of the filling or the surrounding tooth.	Low-Moderate; durable material hardens rapidly; some composite materials show more rapid wear than amalgam. Replacement is usually due to marginal leakage.	Moderate; Slowly dissolves in mouth; easily dislodged.	Moderate; more resistant to dissolving than glass ionomer, but less than composite resin.
Relative Costs to Patient	Low, relatively inexpensive; actual cost of fillings depends upon their size.	Moderate; higher than amalgam fillings; actual cost of fillings depends upon their size; veneers & crowns cost more.	Moderate; similar to composite resin (not used for veneers and crowns).	Moderate; similar to composite resin (not used for veneers and crowns).
Number of Visits Required	Single visit (polishing may require a second visit)	Single visit for fillings; 2+ visits for indirect inlays, veneers and crowns.	Single visit.	Single visit.

Comparisons of InDirect Restorative Dental Materials

	TYPES OF INDIRECT RESTORAT	IVE DENTAL MATERIALS		
COMPARATIVE FACTORS	PORCELAIN (CERAMIC)	PORCELAIN (FUSED-TO-METAL)	GOLD ALLOYS (NOBLE)	NICKEL OR COBALT-CHROME (BASE-METAL) ALLOYS
General Description	Glass-like material formed into fillings and crowns using models of the prepared teeth.	Glass-like material that is "enameled" onto metal shells. Used for crowns and fixed-bridges.	Mixtures of gold, copper and other metals used mainly for crowns and fixed bridges.	Mixtures of nickel, chromium.
Principle Uses	Inlays, veneers, crowns and fixed-bridges.	Crowns and fixed-bridges.	Cast crowns and fixed bridges; some partial denture frameworks.	Crowns and fixed bridges; most partial denture frameworks.
Resistance to Further Decay	Good, if the restoration fits well.	Good, if the restoration fits well.	Good if the restoration fits well.	Good if the restoration fits well.
Estimated Durability (permanent teeth)	Moderate; Brittle material that may fracture under high biting forces. Not recommended for posterior (molar) teeth.	Very good. Less susceptible to fracture due to the metal substructure.	Excellent. Does not fracture under stress; does not corrode in the mouth.	Excellent. Does not fracture under stress; does not corrode in the mouth.
Relative Amount of Tooth Preserved	Good - Moderate. Little removal of natural tooth is necessary for veneers; more for crowns since strength is related to its bulk.	Moderate-High. More tooth must be removed to permit the metal to accompany the porcelain.	Good. A strong material that requires removal of a thin outside layer of the tooth.	Good. A strong material that requires removal of a thin outside layer of the tooth.
Resistance to Surface Wear	Resistant to surface wear; but abrasive to opposing teeth.	Resistant to surface wear; permits either metal or porcelain on the biting surface of crowns and bridges.	Similar hardness to natural enamel; does not abrade opposing teeth.	Harder than natural enamel but minimally abrasive to opposing natural teeth. does not fracture in bulk.
Resistance to Fracture	Poor resistance to fracture.	Porcelain may fracture.	Does not fracture in bulk.	Does not fracture in bulk.
Resistance to Leakage	Very good. Can be fabricated for very accurate fit of the margins of the crowns.	Good – Very good depending upon design of the margins of the crowns.	Very good – Excellent. Can be formed with great precision and can be tightly adapted to the tooth.	Good-Very good – Stiffer than gold; less adaptable, but can be formed with great precision.
Resistance to Occlusal Stress	Moderate; brittle material susceptible to fracture under biting forces.	Very good. Metal substructure gives high resistance to fracture.	Excellent	Excellent
Toxicity	Excellent. No known adverse effects.	Very Good to Excellent. Occasional/rare allergy to metal alloys used.	Excellent; Rare allergy to some alloys.	Good; Nickel allergies are common among women, although rarely manifested in dental restorations.
Allergic or Adverse Reactions	None	Rare. Occasional allergy to metal substructures.	Rare; occasional allergic reactions seen in susceptible individuals.	Occasional; infrequent reactions to nickel.
Susceptibility to Post-Operative Sensitivity	Not material dependent; does not conduct heat and cold well.	Not material dependent; dies not conduct heat and cold well.	Conducts heat and cold; may irritate sensitive teeth.	Conducts heat and cold; may irritate sensitive teeth.
Esthetics (Appearance)	Excellent	Good to Excellent	Poor – yellow metal	Poor – dark silver metal
Frequency of Repair or Replacement	Varies; depends upon biting forces; fractures of molar teeth are more likely than anterior teeth; porcelain fracture may often be repaired with composite resin.	Infrequent; porcelain fracture can often be repaired with composite resin.	Infrequent; replacement is usually due to recurrent decay around margins	Infrequent; replacement is usually due to recurrent decay around margins.
Relative Costs to Patient	High; requires at least two office visits and laboratory services.	High; requires at least two office visits and laboratory services.	High; requires at least two office visits and laboratory services.	High; requires at least two office visits and laboratory services.
Number of Visits Required	Two – minimum; matching esthetics of teeth may require more visits.	Two - minimum; matching esthetics of teeth may require more visits.	Two - minimum	Two - minimum

Glossary of Terms

General Description – Brief statement of the composition and behavior of the dental material

Principle Uses – The types of dental restorations that are made from this material.

Resistance to further decay – The general ability of the material to prevent decay around it.

Longevity/Durability – The probable average length of time before the material will have to be replaced. (This will depend upon many factors unrelated to the material such as biting habits of the patient, their diet, the strength of their bite, oral hygiene, etc.)

Conservation of Tooth Structure – A general measure of how much tooth needs to be removed in order to place and retain the material.

Surface Wear/Fracture Resistance – A general measure of how well the material holds up over time under the forces of biting, grinding, clenching, etc.

Marginal Integrity (Leakage) – An indication of the ability of the material to seal the interface between the restoration and the tooth, thereby helping to prevent sensitivity and new decay.

Resistance to Occlusal Stress – The ability of the material to survive heavy biting forces over time.

Biocompatibility – The effect, if any, of the material on the general overall health of the patient.

Allergic or Adverse Reactions – Possible systemic or localized reactions of the skin, gums and other tissues to the material.

Toxicity – An indication of the ability of the material to interfere with normal physiologic processes beyond the mouth.

Susceptibility to Sensitivity – An indication of the probability that the restored teeth may be sensitive of stimujli (heat, cold, sweet, pressure) after the material is placed in them.

Esthetics – An indication of the degree to which the material resembles natural teeth.

Frequency of Repair or Replacement – An indication of the expected longevity of the restoration made from this material.

Relative Cost – A qualitative indication of what one would pay for a restoration made from this material compared to all the rest.

Number of Visits Required – How many times a patient would usually have to go to the dentist's office in order to get a restoration made from this material.

Dental Amalgam - Filling material which is composed mainly of mercury (43-54%) and varying percentages of silver, tin, and copper (46-57%).